


- CUT-IN REGLET 1" MIN. DEEP, APPLY APPROVED CAULKING AS REQUIRED.
- PRE-SATURATE EDGE OF ALSAN LIQUID MEMBRANE & TUCK INTO JOINT.
- COUNTERFLASHING AS REQUIRED (BY OTHERS)
- PREPARE, LEVEL & PATCH SUBSTRATE W/ ACCEPTABLE PATCHING MORTAR PRIOR TO APPLICATION OF SOPREMA ALSAN LIQUID APPLIED PRIMER AND MEMBRANE (TYP.)
- ALSAN FULLY REINFORCED LIQUID MEMBRANE (FLASHING GRADE) EXTEND 4" (10cm) MIN. HORIZONTALLY ONTO PREPARED AND PRIMED SUBSTRATE.
- ASSURE FULL SATURATION OF FLEECE & CONTACT W/SUBSTRATE.
- ALSAN FULLY REINFORCED LIQUID MEMBRANE (SEE NOTE #2).
- PREPARED AND PRIMED SUBSTRATE (AS REQUIRED)

NOTES:

1. DETAIL TO BE USED IN CONJUNCTION WITH SOPREMA GENERAL REQUIREMENTS, APPLICATION METHODS AND APPROVED DETAILS.
2. A FULLY REINFORCED LIQUID MEMBRANE SYSTEM IS DEFINED AS AN ASSEMBLY CONSISTING OF TWO LIQUID RESIN APPLICATIONS & FABRIC REINFORCEMENT INSTALLED BETWEEN THE RESIN LAYERS. REFER TO DETAIL A-1 FOR ADDITIONAL INFORMATION.

		310 QUADRAL DRIVE WADSWORTH, OHIO 44281 (330) 334-0066					
		TITLE TYPICAL BASE FLASHING					
SCALE	NONE	DWN	PBF	CHK	BS	APPROVAL DATE	3/27/09
DRAWING NUMBER	B-1a					REV	0

** USAGE OF THIS DRAWING IS GOVERNED BY THE TERMS OF SERVICE FOR SOPREMA DETAIL. PLEASE CONSULT THESE TERMS OF SERVICE PRIOR TO UTILIZING THIS DRAWING.