



- MASONRY COPING STONE SET IN MORTAR BED (AS REQUIRED).
- ALSAN LIQUID MEMBRANE COAT W/ BROADCAST QUARTZ SILICA APPLIED OVER MEMBRANE
- TERMINATE ALSAN LIQUID MEMBRANE AT OUTSIDE EDGE OF WALL
- CONCRETE OR MASONRY WALL IN SOUND STRUCTURAL CONDITION.
- PREPARE, LEVEL & PATCH SUBSTRATE W/ ACCEPTABLE PATCHING MORTAR PRIOR TO APPLICATION OF SOPREMA ALSAN LIQUID APPLIED PRIMER AND MEMBRANE (TYP.)
- ALSAN FULLY REINFORCED LIQUID MEMBRANE (FLASHING GRADE) EXTEND 4" (10cm) MIN. HORIZONTAL ONTO PREPARED SUBSTRATE.
- ASSURE FULL SATURATION OF FLEECE & CONTACT W/SUBSTRATE.
- ALSAN FULLY REINFORCED LIQUID MEMBRANE (SEE NOTE #2).
- PREPARED AND PRIMED SUBSTRATE (AS REQUIRED)

4" (10cm)

NOTES:

1. DETAIL TO BE USED IN CONJUNCTION WITH SOPREMA GENERAL REQUIREMENTS, APPLICATION METHODS AND APPROVED DETAILS.
2. A FULLY REINFORCED LIQUID MEMBRANE SYSTEM IS DEFINED AS AN ASSEMBLY CONSISTING OF TWO LIQUID RESIN APPLICATIONS & FABRIC REINFORCEMENT INSTALLED BETWEEN THE RESIN LAYERS. REFER TO DETAIL A-1 FOR ADDITIONAL INFORMATION.
3. APPLY TOP COAT OF ALSAN LIQUID RESIN OVER CURED MEMBRANE & BROADCAST TO REFUSAL WITH KILN-DRIED QUARTZ SILICA AT AREAS WHERE NEW MORTAR WILL CONTACT CURED LIQUID MEMBRANE.

		310 QUADRAL DRIVE WADSWORTH, OHIO 44281 (330) 334-0066					
		TITLE CONCRETE MASONRY WALL FLASHING W/MASONRY COPING STONE					
SCALE	NONE	DWN	PBF	CHK	BS	APPROVAL DATE	3/30/09
DRAWING NUMBER	B-4					REV	0

** USAGE OF THIS DRAWING IS GOVERNED BY THE TERMS OF SERVICE FOR SOPREMA DETAIL. PLEASE CONSULT THESE TERMS OF SERVICE PRIOR TO UTILIZING THIS DRAWING.