



- ALSAN LIQUID MEMBRANE COAT W/ BROADCAST QUARTZ SILICA APPLIED OVER MEMBRANE (SEE NOTE #3).
- MASONRY COPING STONE SET IN MORTAR BED (AS REQUIRED).
- PREPARE, LEVEL & PATCH SUBSTRATE W/ ACCEPTABLE PATCHING MORTAR PRIOR TO APPLICATION OF ALSAN PRIMER AND LIQUID MEMBRANE (TYP.)
- ALSAN FULLY REINFORCED LIQUID MEMBRANE (FLASHING GRADE) EXTEND 4" (10cm) MIN. HORIZONTALLY ONTO PREPARED AND PRIMED SUBSTRATE.
- ASSURE FULL SATURATION OF FLEECE & CONTACT W/ SUBSTRATE.
- 4" WIDE STRIP ALSAN FULLY REINFORCED LIQUID MEMBRANE (FLASHING GRADE) APPLIED OVER ALL JOINTS, ANGLE CHANGES AND VOIDS. FILL JOINTS & VOIDS W/ ACCEPTABLE PATCHING MORTAR OR PASTE PRIOR TO APPLICATION OF ALSAN LIQUID MEMBRANE STRIPS.
- ALSAN FULLY REINFORCED LIQUID MEMBRANE (SEE NOTE #2).
- MIN. 1/4" SOPRABOARD OR APPROVED MIN. 1/2" RECOVERY BOARD (BY OTHERS) SECURELY ATTACHED TO SUBSTRATE.
- MIN. 1" RIGID BOARD INSULATION SECURELY FASTENED TO SUBSTRATE.

NOTES:

1. DETAIL TO BE USED IN CONJUNCTION WITH SOPREMA GENERAL REQUIREMENTS, APPLICATION METHODS AND APPROVED DETAILS.
2. A FULLY REINFORCED LIQUID MEMBRANE SYSTEM IS DEFINED AS AN ASSEMBLY CONSISTING OF TWO LIQUID RESIN APPLICATIONS & FABRIC REINFORCEMENT INSTALLED BETWEEN THE RESIN LAYERS. REFER TO DETAIL A-1 FOR ADDITIONAL INFORMATION.
3. APPLY TOP COAT OF ALSAN LIQUID RESIN OVER CURED MEMBRANE & BROADCAST TO REFUSAL WITH KILN-DRIED QUARTZ SILICA AT AREAS WHERE NEW MORTAR WILL CONTACT CURED LIQUID MEMBRANE.

		310 QUADRAL DRIVE WADSWORTH, OHIO 44281 (330) 334-0066					
		TITLE SINGLE BASE PLY FLASHING W/MASONRY COPING STONE (INSULATED)					
SCALE	NONE	DWN	PBF	CHK	BS	APPROVAL DATE	4/29/09
DRAWING NUMBER	BI-4					REV	0

\*\* USAGE OF THIS DRAWING IS GOVERNED BY THE TERMS OF SERVICE FOR SOPREMA DETAIL. PLEASE CONSULT THESE TERMS OF SERVICE PRIOR TO UTILIZING THIS DRAWING.