

SOPREMA ALSAN RS COLD LIQUID-APPLIED PARKING DECK PROTECTIVE NON-REINFORCED WATERPROOFING SYSTEM SPECIFICATION

PART 1 GENERAL

1.01 SYSTEM DESCRIPTION

- A. The following specification outlines the requirements for an unreinforced, cold fluid-applied, (PMMA) methyl-methacrylate liquid resin protective waterproofing parking deck coating with approved broadcast mineral aggregate and/or textured surfacing and all other ancillary waterproofing work including but not limited to, installation of drains, pipe flashings, penetration flashings, sealants and metal work as specified.
 - 1. All coating materials shall have expansion, to allow for differential movement between the horizontal and vertical surface of the flashed penetration or projection.
 - 2. New coating system MUST provide fast-drying primers to allow substrate preparation, priming and coating application to be completed the same day.
 - 3. Any occupied and/or heated spaces MUST be waterproofed using a fully reinforced system.

1.02 SECTION INCLUDES

- A. Adhered cold fluid-applied (PMMA) methyl-methacrylate liquid resin protective waterproofing coating system including, coating, penetration flashings, base flashings, and expansion joints.
- B. Removal of all existing waterproofing materials
- C. Substrate preparation, cleaning, leveling and patching
- D. Priming
- E. Flashings
- F. Protective wearing/surfacing layer

1.03 RELATED SECTIONS

- A. Supplementary General Conditions
- B. Basic Requirements
- C. Wood Blocking and Nailers
- D. Sheet Metal Flashing and Trim

1.04 REFERENCES

- A. National Roofing Contractors Association (NRCA) Roofing and Waterproofing Manual.
- B. ACI-308 - Recommended Practice for Curing Concrete
- C. ASTM - D638 - Test Methods for Tensile Properties of Plastics
- D. ASTM - D4258 - Standard Practice for Surface Cleaning Concrete for Coatings
- E. ASTM - D4259 - Standard Practice for Abrading Concrete
- F. ASTM - D4541 - Method for Pull-Off Strength of Coatings using Portable Adhesion Tester
- G. ASTM - E96(A) - Test Methods of Moisture Transmission of Material
- H. ASTM E-108, ANSI/UL 790 for fire resistance.
- I. International Concrete Repair Institute Guideline 03732 Concrete Surface Preparation
- J. Steel Structures Painting Council (SSPC)

1.05 SUBMITTALS FOR REVIEW

- A. Coating System Product Data: Provide current standard printed product literature indicating characteristics of coating materials, flashing materials, components, and accessories product specification and installation.
- B. Product Samples: Submit product samples of coating and flashing materials showing color, texture, thickness and surfacing representative of the proposed system for review and approval by the Owners Representative.
- C. Submit sample copies of both the Manufacturer and Applicator warranties for the periods stipulated. Each specimen must be a preprinted representative sample of the issuing company's standard warranty for the system specified.
- D. Submit copies of current Material Safety Data Sheets (MSDS) for all components of the work.
- E. Coating Shop Drawings: Submit shop drawings of cold fluid-applied, (PMMA) methyl-methacrylate liquid resin waterproofing coating system showing all a project plan, size, flashing details, and attachment for review and approval by the Owners Representative and Coating Manufacturer.

1.06 QUALITY ASSURANCE

- A. Coating Manufacturer: Company specializing in manufacturing, cold fluid-applied liquid resin waterproofing coating products as specified in this section with a minimum of five (5) years of documented applications in the United States. Coating Manufacturer shall submit the following certifications for review:
 - 1. Substrates and conditions are acceptable for purpose of providing specified warranty.
 - 2. Materials supplied shall meet the specified requirements.
- B. Applicator: Company specializing in performing the work of this section with (3) years documented experience and approved by system manufacturer for warranted coating installation. Applicator shall submit the following certification for review:
 - 1. Applicator shall submit documentation from the coating manufacturer to verify contractor's status as an approved applicator for warranted installations.
- C. Evaluate moisture content of substrate materials. Constructor shall determine substrate moisture content throughout the work and record with Daily Inspection Reports or other form of reporting acceptable to the Owner or designated Representative, and Coating Manufacturer.
- D. Random tests to determine tensile bond strength of coating to substrate shall be conducted by the Contractor at the job site by the performance of a manual pull test. Contractor shall perform tests at the beginning of the Work, and at intervals as required to assure specified adhesion with a minimum of three (3) tests per 5000 square feet. Smaller areas shall receive a minimum of three (3) tests. Test results shall be submitted to the Owner or his designated Representative and the Coating Manufacturer. Contractor shall immediately notify the Owner or his designated Representative and Coating Manufacturer in the event bond test results are below specified values.
 - 1. Adequate surface preparation will be indicated by tensile bond strength of coating to substrate greater than or equal to 219 psi (1.5 N/mm²) for pedestrian traffic and 300 psi (2.0 N/mm²) for vehicular (low speed) traffic and water flow/containment, as determined by use of an adhesion tester.

2. Adequate surface preparation will be indicated by 135° peel bond strength of coating to substrate such that cohesive failure of substrate occurs before adhesive failure of coating/substrate interface.
 3. In the event the bond strengths are less than the minimum specified, additional substrate preparation is required. Repeat testing to verify suitability of substrate preparation.
- E. Monitor quantities of installed materials. Monitor application of resin mixture, reinforcing fleece and flashing. Perform Work in accordance with manufacturer's instructions.

1.07 REGULATORY REQUIREMENTS

- A. Conform to applicable building and jurisdictional codes for balcony waterproofing assembly and fire resistance requirements.
- B. Comply with requirements of OSHA, NIOSH or local governing authority for work place safety.
- C. Comply with authority or agency "Confined Space Policy" during and throughout all work to be performed.

1.08 PRE-INSTALLATION MEETING

- A. Convene a pre-installation meeting at the job site (1) week before starting work of this section. Require attendance of parties directly affecting work of this section, including but not limited to, [Architect] [Engineer] [Waterproofing Consultant], [Owner's Representative], Waterproofing Contractor, and Coating Manufacturer's Representative. Review waterproofing preparation and installation procedures, coordination and scheduling required with related work, and condition and structural loading limitations of deck/substrate.

1.09 FIELD INSPECTION SERVICES

- A. Manufacturer's technical representative shall provide the following inspections of the coating application:
 1. Job start inspection at the beginning of each phase of the project, to review special detailing conditions and substrate preparation.
 2. Periodic in-progress inspections throughout duration of the project to evaluate coating and flashing application.
 3. Final punch-list inspection at the completion of each phase of the project prior to installation of any surfacing or overburden materials.
 4. Warranty inspection to confirm completion of all punch list items, surfacing, and overburden application.

1.10 DELIVERY, STORAGE, AND PROTECTION

- A. The Contractor together with the Owner or his designated Representative shall define a storage area for all components. The area shall be cool, dry, out of direct sunlight, and in accordance with manufacturer's recommendations and relevant regulatory agencies. Materials shall not be stored in quantities that will exceed design loads, damage substrate materials, hinder installation or drainage.

- B. Store solvent-bearing solutions, resins, additives, inhibitors or adhesives in accordance with the MSDS and/or local fire authority. After partial use of materials replace lids promptly and tightly to prevent contamination.
- C. Roll goods shall be stored horizontally on platforms sufficiently elevated to prevent contact with water and other contaminants. DO NOT use rolls that are wet, dirty or have damaged ends.
- D. Waterproofing materials must be kept dry at all times. If stored outside, raise materials above ground or roof level on pallets and cover with a tarpaulin or other waterproof material. Plastic wrapping installed at the factory should **not** be used as outside storage covers.
- E. Follow manufacturer's directions for protection of materials prior to and during installation. Do not use materials that have been damaged to the point that they will not perform as specified. Fleece reinforcing materials must be clean, dry and free of all contaminants.
- F. Copies of all current MSDS for all components shall be kept on site. Provide any and all crew members with appropriate safety data information and training as it relates to the specific chemical compound he or she may be expected to deal with. Each crew member shall be fully aware of first-aid measures to be undertaken in case of incidents. Comply with requirements of OSHA, NIOSH or local governing authority for work place safety.

1.11 ENVIRONMENTAL REQUIREMENTS

- A. Do not apply waterproofing coating during or with the threat of inclement weather.
- B. Application of cold fluid-applied (PMMA) methyl-methacrylate waterproofing coating may proceed while air temperature is between 32°F (0°C) and 95°F (35°C) providing the substrate is a minimum of 5°F above the dew point.
- C. When ambient temperatures are at or expected to fall below 32°F (0°C), or reach 86°F (30°C) or higher, follow Coating System Manufacturer's recommendations for weather related application procedures.
- D. Ensure that substrate materials are dry and free of contaminants. DO NOT commence with the application unless substrate conditions are suitable. Contractor shall demonstrate that substrate conditions are suitable for the application of the materials.
- E. Where required by the Owner or his designated Representative, Contractor shall implement odor control and elimination measures prior to and during the application of the waterproofing materials. Control/elimination measures shall be field tested at off-hours and typically consists of one (1) or a multiple of the following measures:
 - 1. Sealing of air intakes with activated carbon filters. Install filters in accordance with requirements and recommendations of the filter manufacturer. Seal filters at joints and against building exterior walls to prevent leakage of unfiltered air where required due to size of intake opening. Provide track system to secure filters.
 - 2. Erection and use of moveable enclosure(s) sized to accommodate work area(s) and stationary enclosure for resin mixing station. Enclosure shall be field constructed or pre-manufactured of fire retardant materials in compliance with local code requirements in accordance with requirements of the Owner or his designated Representative. Equipment enclosure(s) with mechanical air intake/exhaust openings and Odor Control Air Cleaners, as required to clean enclosed air volume and to prevent odor migration outside the enclosure. Exhaust opening shall be sealed with activated carbon filter.

3. Placement of odor elimination stations inside and outside of the enclosure(s) as required by field condition, in coordination with the Owner or his designated Representative.
4. Protection of Contractor personnel and occupants of the structure and surrounding buildings as necessary to comply with requirements of OSHA, NIOSH and/or governing local authority.
5. When disposing of all refuse or unused materials, observe all EPA, OSHA or local disposal requirements.

1.12 COORDINATION & PROTECTION

- A. Coordinate the work with the installation of associated metal flashings, accessories, appurtenances, etc. as the work of this section proceeds.
- B. Building components shall be protected adequately (with tarp or other suitable material) from soil, stains, or spills at all hoisting points and areas of application. Contractor shall be responsible for preventing damage from any operation under its Contract. Any such damage shall be repaired at Contractor's expense to Owner's satisfaction or be restored to original condition.
- C. Provide barricades, retaining ropes, safety elements (active/passive) and any appropriate signage required by OSHA, NIOSH, and NSC and/or the Owner or designated Representative.
- D. Protect finished waterproofing coating from damage by other trades. Do not allow waste products containing petroleum, grease, acid, solvents, vegetable or mineral oil, animal oil, animal fat, etc. or direct steam venting to come into direct contact with the coating.

1.13 WARRANTY

- A. Manufacturer's Standard Warranty: Provide five (5) year standard manufacturer's material warranty under provisions of this section.
- B. Submit (2) executed copies of both the manufacturer and any applicator warranties for the periods stipulated, starting from the date of substantial completion. Each warranty must be signed by an authorized representative of the issuing company.

1.14 MATERIAL SUBSTITUTIONS

- A. Materials proposed for use in the performance of the work that are not specified herein must be submitted to the Owner/Owner's Representative for evaluation no later than ten days prior to bid.

PART 2 PRODUCTS

2.01 GENERAL

- A. The products herein specified are totally pre-engineered products of the listed manufacturer and establish criteria for the approval of substitutions. Products must be part of a pre-engineered system, equivalent in function, quality, composition and method of application to be considered for approval as an "Approved Substitute". Substitute materials must meet or exceed the physical performance characteristics of the specified materials. Unsaturated polyesters or single and two component urethane resin systems will not be accepted.

2.02 PRIMERS

- A. Epoxy Primer: Supplied by coating manufacturer; two-component, high solids, and low-odor translucent epoxy primer for use in improving adhesion of coating to substrate surfaces. Monitor application rate and adjust depending on substrate absorbency.
 - 1. Soprema Alsan EPR Primer for use on highly absorbent substrates.
- B. Methyl-Methacrylate Primer: Supplied by coating manufacturer; two-component, high solids (PMMA) methyl-methacrylate resin for use in improving adhesion of coating to various substrate surfaces. Monitor application rate and adjust depending on substrate absorbency.
 - 1. Soprema Alsan RS 222 Primer for use over bituminous surfaces in fully adhered waterproofing coating system.
 - 2. Soprema Alsan RS 276 Primer for use over concrete and wood surfaces in fully adhered waterproofing coating system.

2.03 OTHER RESINS

- A. Patching, Filling and Smoothing Resin: Two-component, with catalyst, cold fluid-applied (PMMA) methyl-methacrylate paste.
 - 1. Soprema Alsan RS Paste for use in filling small cracks, voids and depressions prior to application of Alsan RS resins.
 - 2. Soprema Alsan RS Detailer (micro-fiber enhanced PMMA) for use in flashing small and difficult penetrations and for filling small cracks, voids and depressions to ensure full and proper watertight seal. Use of material must be approved by manufacturer in writing.
- B. Textured Surfacing: Two-component, with catalyst, cold fluid-applied (PMMA) methyl methacrylate resin, with pre-mixed grain, trafficable surface finish.
 - 1. Soprema Alsan RS 290 Textured Finish (medium grain) for use as a pedestrian or vehicular trafficable surface finish in Alsan RS systems.
 - 2. Soprema Alsan RS Textured Coating (large grain) for use as a heavy duty vehicular trafficable ramp surface finish in reinforced and non-reinforced systems.
- C. Finish Resin: Two-component, with catalyst, cold fluid-applied (PMMA) methyl-methacrylate aesthetic finish layer.
 - 1. Soprema Alsan RS 288 Finish for use as a colored finish layer, colored finish layer with Alsan RS Deco Chips broadcasted and as a sealing layer when natural Alsan RS Surfacing Aggregate is used.
 - 2. Soprema Alsan RS 281 Finish for use as a translucent (clear) finish layer over colored Alsan RS Surfacing Aggregate, vinyl chips or other approved aesthetic materials.

2.04 ACCESSORIES

- A. Tools, Accessories, and Cleaners: Supplied and/or approved by coating manufacturer for product installation.
- B. Alsan RS Surfacing Aggregate:

1. Topcoat Slip-Resistant Surfacing Aggregate: Silica sand, ceramic-coated quartz, or specialty aggregate shall be washed, kiln-dried, and dust-free with the following size specification:
 - a. Aesthetic: 0.4 - 0.8 mm
 - b. Bond/Wearing Coat: 1.0 - 1.6 mm
 - c. Pedestrian Traffic: 0.4 - 0.8 mm
 - d. Vehicular Traffic: 0.7 - 1.2 mm
 - e. Soprema Alsan RS Deco Chips: 1/16" + (1.6 mm +)
 2. Leveling and Patching Aggregate: silica sand shall be washed, kiln-dried, and dust-free, suitable for troweling or pourable self-leveling, round grain or angular with the following size specification:
 - a. For voids less than ¼" in depth: 0.4 - 0.8 mm
 - b. For voids ¼" to 2" in depth: 0.7 - 1.2 mm
 - c. Mixing Proportions shall be a ratio of primer to sand at 1:3 by volume or as approved by coating manufacturer.
- C. Backer Rod: Expanded, closed-cell polyethylene foam designed for use with cold-applied joint sealant.
- D. Caulking: Single component, non-sag elastomeric polyurethane sealant, as recommended and supplied by coating manufacturer for use in making airtight and watertight seals where required.
- E. Miscellaneous Fasteners: Appropriate for purpose intended and approved by fastener manufacturer; length required for thickness of material [with metal washers]; as supplied and approved by coating manufacturer.
- F. Drains: Spun/cast aluminum or cast iron roof drain with strainer/grate, as supplied or approved by coating manufacturer.
- G. Temporary and Night Sealant: As recommended or required by coating manufacturer.
- H. Alsan RS Catalyst Powder: White granular powder, based on dibenzoylperoxide, used as a reactive agent to induce curing of all Alsan RS resins.
- J. Alsan RS Liquid Thixo: Thixotropic liquid additive used to increase viscosity of Alsan RS resins.

2.05 WEARING AND SURFACING

- A. Aggregate Slip-Resistant Finish Surfacing: Two-component rapid curing (PMMA) methyl-methacrylate based resin suitable for use to both bond and seal aggregate, as provided by the following Manufacturer:
1. Soprema kiln-dried silica quartz aggregate.
 2. Soprema ceramic colored quartz aggregate.
 3. Soprema Alsan RS 288 Finish color resin.
 4. Soprema Alsan RS 281 Finish translucent resin.
 5. Soprema Alsan RS Deco Chips.
 6. Soprema Alsan RS 290 Textured Finish.

PART 3 EXECUTION

3.01 EXAMINATION

- A. Verify that surfaces and site conditions are ready to receive work.
- B. Verify deck/substrate openings, curbs, and protrusions through deck/substrate, wood cant strips and reglets are in place and solidly set.
- C. Verify deck/substrate is structurally supported, secure and sound.

3.02 PREPARATION OF SUBSTRATE

- A. General: All existing waterproofing materials are to be removed down to the structural deck.
- B. Surfaces to be prepared as a substrate for the new waterproofing system as follows:
 - 1. The contractor shall determine the condition of the existing structural deck/substrate. All defects in the deck or substrate shall be corrected before new waterproofing work commences. Areas of deteriorated deck/substrate, porous or other affected materials must be removed and replaced with new to match existing.
 - 2. Prepare flashing substrates as required for application of new waterproofing coating flashings.
 - 3. Inspect substrates, and correct defects before application of new waterproofing. Fill all surface voids greater than 1/8 inch wide with an acceptable fill material.
 - 4. Remove all ponded water, snow, frost and/or ice from the work substrate prior to installing new waterproofing materials.
 - 5. The final substrate for waterproofing shall be clean, dry, free of loose, spalled or weak material including coatings, mineral aggregate, and flood coat/gravel surfacing, oil, grease, contaminants, abrupt changes in level, waterproofing agents, curing compounds, and free of projections which could damage coating materials.
- C. Concrete:
 - 1. New concrete shall have cured a minimum of 28 days in accordance with ACI-308, or as approved by Waterproofing Manufacturer's Technical Department.
 - 2. New or existing concrete shall be free of oil, grease, curing compounds, loose particles, moss, algae growth, laitance, friable matter, dirt, bituminous products and previous waterproofing materials.
 - 3. New or existing concrete shall be dry with a maximum moisture content of six (6) percent and ninety-six (96) percent relative humidity. Determinations of moisture content shall be performed by the Contractor. Contractor shall be responsible to perform periodic evaluations of moisture content during the work. Moisture evaluation results shall be submitted in writing to the Owner or his designated Representative and Waterproofing manufacturer for acceptance.
 - 4. Where required, concrete shall be abrasively cleaned in accordance with ASTM D4259 to provide a sound substrate free from laitance. Achieve an open concrete surface in accordance with ICRI surface profiles CSP 3-5. When using mechanical methods to remove existing waterproofing products or surface deterioration, the surface profile is

not to exceed ¼ inch (peak to valley).

5. The substrate shall be sound and all spalls, voids and blow holes on vertical or horizontal surfaces must be repaired prior to placement of the primer coat. Ensure all uneven areas are leveled using cementitious or other suitable materials. Repairs are to be done in accordance with the requirements of the Owner or his designated Representative and approved by the Coating Manufacturer.
6. Areas of minor surface deterioration of 0.25" (6 mm) or greater in depth shall be repaired to prevent possible ponding of the system, leading to excessive usage of primer and resin.
7. Extent and location of thin surface patching shall require approval of the Owner or his designated Representative and Waterproofing Manufacturer prior to the application of any system component.
8. For concrete materials with a compressive strength of less than 3,500 psi contact Waterproofing Manufacturer's Technical Department for substrate preparation requirements.

D. Masonry:

1. Walls shall be built with hard kiln dried brick or waterproof concrete block construction.
2. Areas of soft or scaling brick or concrete, faulty mortar joints, or walls with broken, damaged or leaking coping shall be repaired in accordance with the requirements of the Owner or his designated Representative and Coating Manufacturer.

E. Steel/Metal:

1. Clean and prepare metal surfaces to near white metal in accordance with SSPC - SP3 (power tool clean) or as required by coating manufacturer. Extend preparation a minimum of three (3) inches beyond the termination of the coating flashing materials. Notch steel surfaces to provide a rust-stop.
2. In addition to cleaning, all metal surfaces shall be abraded to provide a rough open surface. A wire brush finish is not acceptable.

G. Other Flashing Surfaces:

1. Remove all contaminants as required by coating manufacturer. Surface preparation shall be performed by means approved by Owner or his designated Representative.

H. Optional Finish Leveling, Patching and Crack Preparation:

1. General: Resin/sand mix is the preferred material for all substrate finish leveling, crack and wall/deck preparation and patching. Resin/sand patching mix provides a fast-set time of approximately 45 minutes and does not require surface grinding.
2. Primer/sand mix is an alternative substrate leveling and patching material over horizontal surfaces. Primer/sand patching mix provides a set time of approximately 1 hour, and does not require surface grinding. Primer/sand mix is typically applied in conjunction with general surface priming.
3. Substrate Leveling & Patching: Substrate conditions are to be evaluated by the Contractor, the Owner, or his designated Representative, and Coating Manufacturer.

Perform leveling and patching operations as follows:

- a) Fill cavities on horizontal and low-slope surfaces with a patching mixture of (PMMA) methyl-methacrylate primer and approved kiln-dried sand in a 1:3 primer to sand ratio by volume or with (PMMA) methyl-methacrylate Alsan RS Paste using trowels to apply the resin mortar in place and achieve flat surface.
 - b) Fill cavities on sloped and vertical surfaces with (PMMA) methyl-methacrylate Alsan RS Paste using trowels to apply the resin mortar in place and achieve flat surface.
 - c) Silica sand must be kept absolutely dry during storage and handling.
 - d) Any surface to be leveled or filled must first be primed with an appropriate (PMMA) methyl-methacrylate primer and all Alsan RS resin mortars shall be placed in lifts no greater than the maximum thickness indicated by the manufacturer.
4. Joint and Crack Preparation: Joints, cracks and fractures in the structural deck/substrate shall be prepared as defined below prior to installation of the waterproofing coating. Note: Joints, cracks, and fractures may telegraph through the waterproofing coating.
- a) Non-Moving Cracks: Determine that crack is non-moving. Clean out crack by brushing and oil-free compressed air. Fill crack with (PMMA) methyl-methacrylate Alsan RS Paste. Allow for a minimum of one (1) hour cure or as required by product manufacturer.
 - b) Moving Cracks: Determine that crack is moving. Clean out crack by brushing and oil-free compressed air. Fill crack with (PMMA) methyl-methacrylate Alsan RS Paste. Allow for a minimum of one (1) hour cure or as required by product manufacturer. Apply resin and 4 inch (10 cm) wide strip of membrane (resin and fleece) in strict accordance with Coating Manufacturer's written instructions.

3.03 PRIMER APPLICATION

A. General:

1. Mix and apply two-component (PMMA) methyl-methacrylate primer and epoxy primer in strict accordance with written instructions of Coating Manufacturer. Use only proprietary materials, as supplied by the coating manufacturer.
2. The substrate surface must be dry, with any remaining dust or loose particles removed using clean, dry, oil-free compressed air, industrial vacuum, cloth wipe or a combination of methods.
3. Do not install primer on any substrate containing newly applied and/or active asphalt, coal-tar pitch, creosote or penta-based materials unless approved in writing by Coating Manufacturer. Some substrates may require additional preparation before applying primer.

B. Mixing of Standard Two-Component (PMMA) Methyl-Methacrylate Primers:

1. Premix primer thoroughly with a spiral agitator or stir stick. Add pre-measured catalyst amount into mixed primer container and mix the components for approximately 2 minutes with a clean spiral agitator on slow speed or stir stick without creating any

bubbles or streaks. DO NOT AERATE. The primer solution should be a uniform color, with no light or dark streaks present.

2. Do not thin primer. Determine required primer coverage for each substrate material/condition and apply in strict accordance with written instructions of Coating Manufacturer.
3. Mix only that amount of primer that can be used within 15 minutes.

C. Mixing of Standard Two-Component Epoxy Primer:

1. Mix A and B components together with a spiral agitator or stir stick. Use slow speed. DO NOT AERATE. The primer solution should be a uniform color, with no light or dark streaks present.
2. Do not thin primer. Determine required primer coverage for each substrate material/condition and apply in strict accordance with written instructions of Coating Manufacturer.
3. Mix only that amount of primer that can be used within 15 minutes.

D. Application of Primers:

1. Apply PMMA primer at the minimum rate of approximately 0.037 kg/sf (0.4 kg/m²). Apply epoxy primer at the minimum rate of approximately 0.028 kg/sf (0.3 kg/m²)
2. Roll or brush the primer evenly onto the surface to fully saturate the substrate in one application. Do not allow primer to pond or collect in low areas.
3. Apply primer only up to the edge of the coating flashing terminations. Primer application past the coating terminations requires surfacing with an approved material.
4. For (PMMA) methyl-methacrylate primer applications over cementitious substrates where protection from substrate wetness is required, apply primer coat at a heavier application rate until pore saturation is achieved.
5. For all Alsan EPR primer applications, apply kiln-dried sand into the final coat of Alsan EPR primer while still wet at the rate of 30 lbs. per 100 square feet (1.5 kg/m²). Use quartz size # 0 (0.4 – 0.8 mm).
6. Allow standard (PMMA) methyl-methacrylate primers to cure for a minimum of thirty (30) minutes before coating application. Allow epoxy-based quick-dry primers to cure for a minimum of one (1) hour before coating application. Coating must be applied to primer only when completely dry and without tack.
7. Premature exposure to moisture may require removal and application of new primer. DO NOT apply new primer over exposed primer older than six (6) months, primer prematurely exposed to moisture, or primer used as temporary waterproofing, unless approved in writing by the Coating Manufacturer.

E. Disposal of Primer:

1. Cured primer may be disposed of in standard landfills. This is accomplished by thoroughly mixing with catalyst powder.

2. Uncured primer is considered a hazardous material and must be handled as such, in accordance with local, state and federal regulation. Do not through uncured resin away.

3.04 FLASHING APPLICATION

A. General:

1. Install urethane caulk in accordance with the requirements/recommendations of the Coating Manufacturer and as depicted on standard drawings and details.
2. Install caulking before installing the wearing/surfacing coating to minimize foot traffic over newly installed field coating.
3. All flashings shall be installed concurrently with the waterproofing coating as the job progresses. Temporary flashings are not allowed without prior written approval from the Coating manufacturer. Should any water penetrate the new waterproofing coating because of incomplete flashings, the affected area shall be removed and replaced at the contractor's expense.
4. Surfacing height shall be at least as high as the potential water level that could be reached as a result of a deluging rain and/or poor slope. Do not flash over existing through-wall flashings, weep holes and overflow scuppers.
5. Coating flashings shall be fabricated with primer appropriate for the substrate surface.
6. All flashings shall be terminated as required by the Coating Manufacturer.

B. Metal Flashing – General:

1. Metal flashings shall be fabricated in accordance with the current recommendations of SMACNA and in accordance with standard drawings and project details.
2. Metal flashing flanges to which coating is to be bonded shall be a minimum of four (4) inches in width, and secured to the substrate six (6) inches on center staggered with fasteners appropriate to the substrate type. The flanges shall be provided with a roughened surface that has been cleaned of all oil and other residue.
3. Metal edges that will be overlaid with coating shall be provided with a 1/4" min. hemmed edge.
4. Apply primer and wearing/surfacing coating to metal flange, extending coating to outside face of metal edging, and to vertical face of metal base/curb flashing.

C. Pipes, Conduits, and Unusually Shaped Penetrations:

1. Flash all penetrations using urethane caulk.

D. Drains and Scuppers:

1. Acceptable drain and scupper materials are cast iron, cast aluminum, and copper.
2. Connect new drains and scuppers to existing storm sewer system.
3. Alternatively, replace all broken or damaged parts of existing drains and scuppers, or

provide and install an acceptable insert.

4. Flash drains and scuppers using urethane caulk..
5. Wearing/surfacing material shall extend four (4) inches minimum onto drain, scupper, or insert flange.
6. Install clamping ring if provided as part of the drain or scupper design. Install a strainer basket to prevent debris from clogging the drainage line.

E. Walls, Curbs and Base Flashings:

1. Wall, curb and base flashings shall be installed to solid substrate surfaces only. Adhering to gypsum-based panels, cementitious stucco, synthetic stucco, wood or metal siding, and other similar materials is not acceptable.
2. Flash all walls, curbs and base flashings, changes of direction, etc. using urethane caulk.

F. Field Fabricated Control or Expansion Joint Flashing:

1. Fill control or expansion joints with urethane caulk and a compressible foam or rubber insert. Grind or otherwise bevel the inside edges of the joint opening to provide a smooth transition edge for the caulk.
2. Optional: Construct an expansion joint of cold fluid-applied (PMMA) methyl-methacrylate waterproofing coating. Flashing typically consists of polyester reinforcing fleece bottom layer looped into the joint as a cradle, a compressible foam or rubber insert at 25% compression fitted into the joint, and a polyester fleece top layer applied over the joint. Extend fleece layer two (2) inches minimum onto the field substrate on both sides of the joint.
3. Apply the wearing/surfacing coating over the entire joint area.

G. Drip Edges and Gravel Stops:

1. Metal drip edges and gravel stops shall be installed to solid substrate surfaces only. Securement to gypsum-based panels, cementitious stucco, synthetic stucco, wood or metal siding or coping, and other similar materials are not acceptable.
2. Caulk all metal drip edges and gravel stops. Apply wearing/surfacing coating.

3.05 WEARING AND SURFACING

A. Aggregate Slip-Resistant Finish Surfacing

1. Where specified, provide and install Coating Manufacturer's approved two-component (PMMA) methyl-methacrylate based finish surfacing coating with slip-resistant aggregate additive applied over clean, fully cured coating.
2. Premix all Alsan RS resins thoroughly for approximately 2 minutes with a clean spiral agitator on slow speed or stir stick without creating any bubbles or streaks until material is consistent in color.
3. Add the pre-measured Catalyst Powder to resin and mix with the same agitator for 2

minutes or until the powder is completely mixed. The catalyst is completely dissolved when there are no white specs remaining.

4. Apply Alsan RS 288 Finish resin at a minimum rate of approximately 0.065 kg/sf (0.7 kg/m²). Product shall be applied with a lambswool roller to achieve a smooth and level surface. Broadcast natural kiln-dried sand or colored quartz aggregate surfacing at approximate rate of 0.46 kg/sf; 1.0 lbs/sf; (5.0 kg/m²) or as recommended by manufacturer into wet surface of coating to provide slip-resistant protective surfacing. Avoid any traffic for a minimum of two (2) hours to allow for surfacing to cure. Remove all excess and loose quartz aggregate using a broom, vacuum and/or oil-free blower. Seal natural quartz silica aggregate surfacing with an additional Alsan RS 288 Finish pigmented coating application at a rate of approximately 0.065 kg/sf (0.7 kg/m²). Seal colored quartz silica aggregate surfacing with an additional Alsan RS 281 Finish translucent coating application at a rate of approximately 0.065 kg/sf (0.7 kg/m²). Products shall be applied with a rubber flat blade squeegee and a lambswool roller to achieve a uniform surface. Avoid any traffic for a minimum of one (1) hour to allow for coating to cure.
5. Optional Textured Surfacing: Apply Alsan RS 290 Textured Finish at a minimum rate of approximately 0.19 kg/sf (2.0 kg/m²). Product shall be applied with a smoothing trowel and/or a lambswool roller to achieve a uniform surface. Avoid any traffic for a minimum of one (1) hour to allow for coating to cure.
6. Optional Alsan RS Deco Chips: Apply Alsan RS 288 Finish coating at a rate of approximately 0.056 kg/sf (0.6 kg/m²). Product shall be applied with a lambswool roller to achieve a smooth and level surface. Broadcast the specified Alsan RS Deco Chips into the wet color finish by hand or hopper spray gun at a minimum rate of 0.019 kg/sf (0.2 kg/m²). Allow to cure and sweep away excess chips. Avoid any traffic for a minimum of one (1) hour to allow for surfacing to cure.
7. For Ramps: Heavy duty ramps requiring a rough surface texture, apply Alsan RS Textured Coating at a minimum rate of approximately 0.325 kg/sf (3.5 kg/m²). Product shall be applied with a smoothing trowel to achieve a uniform surface. Avoid any traffic for a minimum of one (1) hour to allow for coating to cure.

3.06 TEMPORARY CLOSURES & WATERSTOPS

- A. Contractor shall be responsible to ensure that moisture does not damage any completed section of the new waterproofing system. Completion of flashings, terminations, and temporary closures shall be completed as required to provide a watertight condition. All temporary closures shall be made as recommended or required by the coating manufacturer.

3.07 PROTECTION

- A. Upon completion of waterproofing and flashings (including all associated work), institute appropriate procedures for surveillance and protection of waterproofing during remainder of construction period. Protect all areas where coating has been installed.

3.08 CLOSEOUT

- A. Correction of Work:
 1. Work that does not conform to specified requirements including tolerances, slopes, and finishes shall be corrected and/or replaced. Any deficiencies of coating application, termination and/or protection as noted during the Coating Manufacturer's

inspections shall be corrected and/or replaced at Contractor's expense.

B. Clean-Up:

1. Site clean-up, including both interior and exterior building areas that have been affected by construction, shall be restored to preconstruction condition.

END OF SECTION