



SOPRALAST TV COPPER

SOPRALAST TV COPPER (58)

Order No. 05191

DESCRIPTION

SOPRALAST TV COPPER is fiberglass scrim reinforced roofing membranes combined with selected SBS modified bitumen, with an underside plastic burn-off film and a topside metal facing to form heat-welded, metal-clad membranes. When heat-welding, use a damp sponge or mop to cool the metal film immediately after application. See published Specifications and Approved Details.

COMPOSITION & PACKAGING

Product/ Property	SOPRALAST TV COPPER
Reinforcement	fiberglass
Elastomeric Bitumen	selected blend of bitumen & SBS thermoplastic polymers
Top Surface	Copper
Bottom Surface	Plastic film
Approximate Nominal Thickness	140 mils (3.5 mm)
Approximate Roll Coverage	97.5 ft ² (9.1 m ²)
Side Lap	3" (25 mm)
End Lap	6" (152 mm)
Roll Length	33' (10 m)
Roll Width	39" (1 m)
Approximate Roll Weight	103 lbs (46.7 kg)
Rolls per Pallet*	25
*Rolls stocked upright on pallet	

APPROVALS

See Underwriters Laboratories Inc. File #R11436, FM Approvals, ICC/ES, Miami-Dade County or Florida Building Code Product Approval Listings for current Approved Roof Assembly combinations. Soprema is ISO-9001:2000 Certified.

WARRANTY

Contact your local SOPREMA representative for project warranty offerings.



PHYSICAL PROPERTIES

Physical Property per ASTM D 6298	MD	XD
Tensile - Max Load at $0 \pm 3.6^{\circ}\text{F}$ lbf/in	200	175
Elongation at $0 \pm 3.6^{\circ}\text{F}$ %	12	10
Tensile - Max Load at $73.4 \pm 3.6^{\circ}\text{F}$ lbf/in	136	134
Elongation at $73.4 \pm 3.6^{\circ}\text{F}$ %	8	8
Tear Strength at $73.4 \pm 3.6^{\circ}\text{F}$ lbf	130	130
Low Temperature Flex $^{\circ}\text{F}$ max	-15	-15
Dimensional Stability % max	<0.2	<0.2
Compound Stability Temp F	225	225
Minimum values before and after Heat Conditioning Test results for manufacturing plant in Wadsworth, OH		

GENERAL

SOPREMA is a Certified ISO 9001:2000 worldwide producer of bituminous membranes with factories in Europe and North America. Waterproofing sheets have been produced by SOPREMA since 1908. Today, through a special mixture of components, SOPREMA membranes redefine the qualities indispensable to a high performance roof membrane: elasticity, flexibility, heat & fatigue resistance.

SOPREMA SBS modified bitumen membrane assemblies typically consist of base and top ply membranes that have specific type reinforcements in order to meet specific ASTM Standards. The two ply system provides a resistance to punctures and tears, as well as ensuring an effective distribution of stress points. The two ply system operates in a homogeneous fashion. The bitumen in each layer moves uniformly to offer continuous protection.