



ELASTOPHENE SANDED 3.0 mm

ELASTOPHENE SANDED 3.0 mm (25A)

Order No. 00251

DESCRIPTION & APPLICATION

Elastophene 3.0mm is designed for use in multi-layer modified bitumen roof systems and plaza waterproofing assemblies. Elastophene Sanded 3.0 mm is composed of selected SBS modified bitumen applied onto a glass mat reinforcement with high brush sanded bottom and top surface. Elastophene Sanded 3.0 mm field base membrane ply is adhered to a properly prepared, clean, dry and/or primed (where required) substrate by using hot asphalt or cold adhesive. Optional inner ply(s) or the field cap membrane ply is bonded to the properly prepared, clean, dry and/or primed (where required).

A self-adhesive cap sheet can also be installed when the Elastophene surface is properly prepared with the appropriate Soprema Primer and Soprema Sealant is applied to all side and end lap edges not having a bitumen bleed-out. See published Specifications and Approved Details.

COMPOSITION & PACKAGING

Product/ Property	ELASTOPHENE SANDED 3.0 mm
Reinforcement	fiberglass reinforcement
Elastomeric Bitumen	selected blend of bitumen and SBS thermoplastic polymers
Topside	lightly sanded
Underside	lightly sanded
Approximate Nominal Thickness	120 mils (3.0 mm)
Approximate Roll Coverage	97.5 ft ² (9.1 m ²)
Side Lap	3" (76 mm)
End Lap	6" (152 mm)
Roll Length	33 ft (10 m)
Roll Width	39" (1 m)
Approximate Roll Weight	90 lbs (40.8 kg)
Rolls per Pallet*	30

* Rolls stocked upright on pallets

WARRANTY

Contact your local SOPREMA representative for project warranty offerings.



PHYSICAL PROPERTIES

Physical Property per ASTM D 6163, Type I, Grade S	MD	XD
Tensile - Max Load at 0 ± 3.6°F lbf/in	116	104
Elongation at 0 ± 3.6°F %	4.2	4.0
Tensile - Max Load at 73.4 ± 3.6°F lbf/in	57	57
Elongation at 73.4 ± 3.6°F %	4.0	4.0
Tear Strength at 73.4 ± 3.6°F lbf	82	73
Low Temperature Flex °F max	-15	-15
Dimensional Stability % max	<0.1	<0.1
Compound Stability Temp F	230	230
Granule Embedment g/max	NA	NA

Minimum values before and after Heat Conditioning
Test results for manufacturing plant in Wadsworth, OH

APPROVALS

See Underwriters Laboratories Inc. File #R11436, FM Approvals, ICC/ES, Miami-Dade County or Florida Building Code Product Approval Listings for current Approved Roof Assembly combinations. Soprema is ISO-9001:2000 Certified.

Elastophene Sanded 3.0mm is approved by FM Approvals for use in roof systems over insulated and non-insulated approved roof deck constructions, subject to FM conditions and limitations.

Elastophene Sanded 3.0mm ballasted roof systems have been classified by Underwriters Laboratories as Class A roofing systems (TGFU Roof Systems) over insulated and non-insulated combustible and non-combustible roof decks.

GENERAL

SOPREMA is a Certified ISO 9001:2000 worldwide producer of bituminous membranes with factories in Europe and North America. Waterproofing sheets have been produced by SOPREMA since 1908. Today, through a special mixture of components, SOPREMA membranes redefine the qualities indispensable to a high performance roof membrane: elasticity, flexibility, heat & fatigue resistance.

SOPREMA SBS modified bitumen membrane assemblies typically consist of base and top ply membranes that have specific type reinforcements in order to meet specific ASTM Standards. The two ply system provides a resistance to punctures and tears, as well as ensuring an effective distribution of stress points. The two ply system operates in a homogeneous fashion. The bitumen in each layer moves uniformly to offer continuous protection.