



# ELASTOPHENE GR



ELASTOPHENE GR (41) (FR Low Slope) Order No. 01064\*

\*Cap sheet order numbers are for WHITE CAP SHEETS ONLY. Contact Customer Service or your Sales Representative for other available cap sheet colors and special order requirements.

## DESCRIPTION & APPLICATION

Elastophene GR is composed of selected SBS modified bitumen applied onto a glass mat reinforcement with high brush sanded bottom and granule top surface. Elastophene GR field cap membrane ply is adhered to a properly prepared, clean, dry and/or primed (where required) substrate by using hot asphalt or cold adhesive.

See published Specifications and Approved Details.

## COMPOSITION & PACKAGING

Product/ Property	ELASTOPHENE GR
Reinforcement	fiberglass reinforcement
Elastomeric Bitumen	selected blend of bitumen and SBS thermoplastic polymers
Topside	granules
Underside	lightly sanded
Approximate Nominal Thickness	136 mils (3.4 mm)
Approximate Roll Coverage	97.5 ft <sup>2</sup> (9.1 m <sup>2</sup> )
Side Lap	3" (76 mm)
End Lap	6" (152 mm)
Roll Length	33 ft (10 m)
Roll Width	39" (1 m)
Approximate Roll Weight	95 lbs (43.1 kg)
Rolls per Pallet*	30

\* Rolls stocked upright on pallets

## APPROVALS

See Underwriters Laboratories Inc. File #R11436, FM Approvals, ICC/ES, Miami-Dade County or Florida Building Code Product Approval Listings for current Approved Roof Assembly combinations. Soprema is ISO-9001:2009 Certified.

## WARRANTY

Contact your local SOPREMA representative for project warranty offerings.




## PHYSICAL PROPERTIES

Physical Property per ASTM D 6163, Type I, Grade G	MD	XD
Tensile - Max Load at 0 ± 3.6°F lbf/in	116	104
Elongation at 0 ± 3.6°F %	4.2	4.0
Tensile - Max Load at 73.4 ± 3.6°F lbf/in	57	57
Elongation at 73.4 ± 3.6°F %	4.0	4.0
Tear Strength at 73.4 ± 3.6°F lbf	82	73
Low Temperature Flex °F max	-15	-15
Dimensional Stability % max	<0.1	<0.1
Compound Stability Temp F	215	215
Granule Embedment g/max	0.8	0.8
Minimum values before and after Heat Conditioning Test results for manufacturing plant in Wadsworth, OH		

## GENERAL

SOPREMA is a Certified ISO 9001:2008 worldwide producer of bituminous membranes with factories in Europe and North America. Waterproofing sheets have been produced by SOPREMA since 1908. Today, through a special mixture of components, SOPREMA membranes redefine the qualities indispensable to a high performance roof membrane: elasticity, flexibility, heat & fatigue resistance.

SOPREMA SBS modified bitumen membrane assemblies typically consist of base and top ply membranes that have specific type reinforcements in order to meet specific ASTM Standards. The two ply system provides a resistance to punctures and tears, as well as ensuring an effective distribution of stress points. The two ply system operates in a homogeneous fashion. The bitumen in each layer moves uniformly to offer continuous protection.

		<u>Initial</u>	<u>Weathered</u>
	Solar Reflectance	0.28	0.25
	Thermal Emittance	0.86	0.90
	Rated Product ID Number	0772-0019	
	Licensed Seller ID Number	0772	
	Classification	Production Line	
Cool Roof Rating Council ratings are determined for a fixed set of conditions, and may not be appropriate for determining seasonal energy performance. The actual effect of solar reflectance and thermal emittance on building performance may vary.			
Manufacturer of product stipulates that these ratings were determined in accordance with the applicable Cool Roof Rating Council procedures.			

CA Title 24 Compliant Initial/Weathered - CRRC Rated	Reflectivity 0.28 / 0.25	Emmissivity 0.86 / 0.90
LEED	Recycled Content 0%	
	Production Location: Wadsworth, OH, Gulfport, MS & Chilliwack, BC	
Solar Reflective Index(SRI)		
	Initial	Weathered
	27.4	25.3