



# COLVENT FLAM SA

COLVENT FLAM SA (79B)

Order No. 00371

## DESCRIPTION & APPLICATION

Colvent Flam SA is a semi-adhered field base membrane ply with a special elastomeric modified bitumen blend of SBS and other polymers. This is applied onto a glass mat reinforcement with a specific venting pattern of self-adhesive ribbon strips bonded to the underside along with a plastic film topside. The membrane is bonded to the properly prepared and/or primed substrate. The Colvent Flam SA underside SBS self-adhesive strips are covered with a release film. When this release film is removed, the self-adhesive strips are matted onto the substrate using applied pressure.

The ribbon strip-venting design enhances stress distribution at the substrate while the vapor diffusion reduces the chance of blistering. The plastic film on the Colvent Flam SA membrane topside allows for inner ply or cap sheet membranes to be bonded by the heat welding application method.

General application methods include applying pressure to all the membrane roll ends to insure proper bonding to the substrate. Side laps with burn-off film are sealed when the burn-off film is melted away as the roll is being adhered. The side laps are mated together and sealed using applied pressure. End laps and "T" joints are sealed using hot air welding techniques or where applicable heat welding.

See published Specifications and Approved Details.

## COMPOSITION & PACKAGING

Product/ Property	COLVENT FLAM SA
Reinforcement	fiberglass
Elastomeric Bitumen	selected blend of bitumen and SBS thermoplastic polymers
Topside	plastic film
Underside	self-adhesive bitumen ribbon strips with release film
Approximate Nominal Thickness	90 mils (2.2 mm)
Approximate Roll Coverage	147 ft <sup>2</sup> (13.6 m <sup>2</sup> )
Side Lap	3" (76 mm)
End Lap	6" (152 mm)
Roll Length	49 ft (15 m)
Roll Width	39" (1 m)
Approximate Roll Weight	98 lbs (44.5 kg)
Rolls per Pallet*	30
* Rolls stocked upright on pallets	



## PHYSICAL PROPERTIES

Physical Property per ASTM D 6163, Type I, Grade S	MD	XD
Tensile - Max Load at $0 \pm 3.6^{\circ}\text{F}$ lbf/in	116	104
Elongation at $0 \pm 3.6^{\circ}\text{F}$ %	4.2	4.0
Tensile - Max Load at $73.4 \pm 3.6^{\circ}\text{F}$ lbf/in	57	57
Elongation at $73.4 \pm 3.6^{\circ}\text{F}$ %	4.0	4.0
Tear Strength at $73.4 \pm 3.6^{\circ}\text{F}$ lbf	82	73
Low Temperature Flex $^{\circ}\text{F}$ max	-15	-15
Dimensional Stability % max	<0.1	<0.1
Compound Stability Temp F	250	250
Granule Embedment g/max	NA	NA
Minimum values before and after Heat Conditioning Test results for manufacturing plant in Wadsworth, OH		

## APPROVALS

See Underwriters Laboratories Inc. File #R11436, FM Approvals, ICC/ES, Miami-Dade County or Florida Building Code Product Approval Listings for current Approved Roof Assembly combinations. Soprema is ISO-9001:2008 Certified.

## GENERAL

SOPREMA is a Certified ISO 9001:2008 worldwide producer of bituminous membranes with factories in Europe and North America. Waterproofing sheets have been produced by SOPREMA since 1908. Today, through a special mixture of components, SOPREMA membranes redefine the qualities indispensable to a high performance roof membrane: elasticity, flexibility, heat & fatigue resistance.

SOPREMA SBS modified bitumen membrane assemblies typically consist of base and top ply membranes that have specific type reinforcements in order to meet specific ASTM Standards. The two ply system provides a resistance to punctures and tears, as well as ensuring an effective distribution of stress points. The two ply system operates in a homogeneous fashion. The bitumen in each layer moves uniformly to offer continuous protection.

## WARRANTY

Contact your local SOPREMA representative for project warranty offerings.