



# SOPRALENE 350 FR GR

SOPRALENE 350 FR GR (49A)

Order No. \*

\*Contact Customer Service for order number and availability.

## DESCRIPTION & APPLICATION

Sopralene 350 FR GR cap ply is composed of selected SBS modified bitumen applied onto a non-woven polyester reinforcement with sand on the underside and a colored granule topside surface.

The Sopralene 350 FR GR field and flashing cap membrane ply is adhered to a properly prepared, clean, dry and/or primed (where required) base or ply membrane by using the hot asphalt or cold adhesive application methods. Note: Soprema does not recommend cold adhesive application of this product.

See published Specifications and Approved Details.

## COMPOSITION & PACKAGING

Product/ Property	SOPRALENE 350 FR GR
Reinforcement	polyester
Elastomeric Bitumen	selected blend of bitumen and SBS thermoplastic polymers
Topside	colored granules
Underside	sanded
Approximate Nominal Thickness	200 mils (5.0 mm)
Approximate Roll Coverage	76 ft <sup>2</sup> (7 m <sup>2</sup> )
Side Lap	3" (76 mm)
End Lap	6" (152 mm)
Roll Length	26 ft (7 m)
Roll Width	39" (1 m)
Approximate Roll Weight	110 lbs (50 kg)
Rolls per Pallet*	25
* Rolls stocked upright on pallets	

## WARRANTY

Contact your local SOPREMA representative for project warranty offerings.



## PHYSICAL PROPERTIES

Physical Property per ASTM D 6164, Type II, Grade G	MD	XD
Tensile - Max Load at 0 ± 3.6°F lbf/in	187	150
Elongation at 0 ± 3.6°F %	34	38
Tensile - Max Load at 73.4 ± 3.6°F lbf/in	175	133
Elongation at 73.4 ± 3.6°F %	53	57
Tear Strength at 73.4 ± 3.6°F lbf	202	156
Low Temperature Flex °F max	-15	-15
Dimensional Stability % max	<0.5	<0.5
Compound Stability Temp F	230	230
Granule Embedment g/max	0.8	0.8

Minimum values before and after Heat Conditioning  
Test results for manufacturing plant in Wadsworth, OH

## APPROVALS

See Underwriters Laboratories Inc. File #R11436, FM Approvals, ICC/ES, Miami-Dade County or Florida Building Code Product Approval Listings for current Approved Roof Assembly combinations. Soprema is ISO-9001:2000 Certified.

## GENERAL

SOPREMA is a Certified ISO 9001:2000 worldwide producer of bituminous membranes with factories in Europe and North America. Waterproofing sheets have been produced by SOPREMA since 1908. Today, through a special mixture of components, SOPREMA membranes redefine the qualities indispensable to a high performance roof membrane: elasticity, flexibility, heat & fatigue resistance.

SOPREMA SBS modified bitumen membrane assemblies typically consist of base and top ply membranes that have specific type reinforcements in order to meet specific ASTM Standards. The two ply system provides a resistance to punctures and tears, as well as ensuring an effective distribution of stress points. The two ply system operates in a homogeneous fashion. The bitumen in each layer moves uniformly to offer continuous protection.