


ALSAN RS FLASHING SYSTEM

RAPID CURE LIQUID MEMBRANE FLASHING SYSTEM



PRODUCT DETAILS

ALSAN RS PRIMER

Primer for improving substrate adhesion

ALSAN RS 230 FLASH

Single component polyurethane waterproofing resin

Please refer to applicable product data sheets for additional information.

SUBSTRATE PREPARATION

Refer to substrate preparation and priming schedule. Remove existing paint and finishes etc. by mechanical means.

Ensure that the prepared surface is clean, dry and free from dust, laitance, grease, oil and any other contaminants.

Concrete substrate should have a maximum moisture content of 1.5 kg/100m²/24h (ASTM F1869) and internal content of 75 % RH (ASTM F2170).

Acceptance of the substrate is the sole decision of the owner or appointed representative.

PRIMING

ALSAN RS PRIMER:

Apply with a lambswool roller (0.4 kg/m² min.).

Rainproof after approx. 25 minutes.

Can be walked upon/next coat applied after approx. 45 minutes.

PRODUCT PREPARATION

Apply an even layer of ALSAN RS 230 (2.0 kg/m² min.) with a lambswool roller or notched squeegee.

Roll ALSAN RS FLEECE reinforcement into the wet resin, pressing trapped air free using the lambswool roller, ensuring a minimum 50mm overlap between the reinforcement sheets.

Apply ALSAN RS 230 (1.0 kg/m² min.) wet on wet to ensure full saturation of the fleece.

Rainproof after approx. 30 minutes.

Can be walked upon/next coat applied after approx. 45 minutes.

Able to withstand stress after approx. 2 hours.

TRAFFICABLE SURFACING

Not applicable.

COMPLETION

Upon completion of new installation (including all associated work), institute appropriate procedures for surveillance and protection of finished work during remainder of construction period. Protect all areas where coating has recently been installed. Notify the Owner and the Manufacturer when finished. Coordinate final inspection by Manufacturer. Complete all repairs or requests promptly. Comply with all paperwork and payment requirements necessary to acquire the specified warranty.

SOPREMA